

# LOCTITE<sup>®</sup> PC 7202<sup>™</sup>

Known as LOCTITE<sup>®</sup> Fixmaster<sup>®</sup> Marine Chocking or LOCTITE<sup>®</sup> 7202  
August 2019

## PRODUCT DESCRIPTION

LOCTITE<sup>®</sup> PC 7202<sup>™</sup> provides the following product characteristics:

<b>Technology</b>	Epoxy
<b>Chemical Type</b>	Epoxy
<b>Appearance</b>	Orange or green liquid
<b>Components</b>	Two components - requires mixing
<b>Mix Ratio, (by volume) Resin : Hardener</b>	100 : 11.6
<b>Mix Ratio, (by weight) Resin : Hardener</b>	100 : 6.9
<b>Cure</b>	Room temperature cure
<b>Application</b>	Flooring & grout
<b>Specific Benefit</b>	<ul style="list-style-type: none"> <li>Withstands temperatures from -30°C up to 121 °C</li> <li>Non-shrinking</li> <li>Chemical resistant</li> <li>100 % solids epoxy system</li> <li>Vibration resistant</li> <li>Self-leveling</li> <li>Allows flow into hard to reach areas</li> <li>Application versatility</li> </ul>

LOCTITE<sup>®</sup> PC 7202<sup>™</sup> is a two-part epoxy chocking systemIt is recommended for the installation of main engines and other equipment. Its high compressive strength withstands maximum loadsTypical applications include installation of main engines, drive engines, winches, hoists, and deck mounted equipment

## TYPICAL PROPERTIES OF UNCURED MATERIAL

### Resin (Orange):

Viscosity, Brookfield - RVDV3,25°C,mPa·s (cP):	
Spindle 7,, speed 20 rpm	80,000 to 110,000
Weight Per Gallon, lbs/gal	13.3 to 14.0

### Resin (Green):

Viscosity, Brookfield - RVDV3,25°C,mPa·s (cP):	
Spindle 7,, speed 20 rpm	85,000 to 105,000
Weight Per Gallon, lbs/gal	13.5 to 14.3

### Hardener:

Viscosity, Cone & Plate, 25 °C, mPa·s (cP):	
Shear rate 3,000 s <sup>-1</sup>	32.6

### Mixed:

Density @ 25 °C, ISO 1675, g/cm<sup>3</sup> 1.5

Coverage 636 cm<sup>3</sup> per 1 kg  
(17.6 in<sup>3</sup> per 1 lb)

## TYPICAL CURING PERFORMANCE

### Curing Properties

Cure Time @ 25 °C, hours	24
Working Time @ 25 °C, minutes	10 to 15
Gel Time (Orange) @ 25 °C, minutes: 400 g mass	33 to 47
Gel Time (Green) @ 25 °C, minutes: 400 g mass	38 to 45

## TYPICAL PROPERTIES OF CURED MATERIAL

Cured for 24 hours @ 25 °C

### Physical Properties:

Shore Hardness, ISO 868, Durometer D	90
Tensile Strength, ISO 527-2	N/mm <sup>2</sup> 38 (psi) (5,500)
Compressive Strength, ISO 604	N/mm <sup>2</sup> 110 (psi) (16,000)
Compressive Modulus, ISO 604	N/mm <sup>2</sup> 2,760 (psi) (400,000)
Tensile Modulus, ASTM D638	N/mm <sup>2</sup> 8,400 (psi) (1,220,000)
Glass Transition Temperature TMA ISO 11359-2, °C	110
Coefficient of Thermal Expansion, ISO 11359-2 K <sup>-1</sup> :	
Below Tg	47×10 <sup>-06</sup>
Above Tg	110×10 <sup>-06</sup>
Barcol Hardness, ASTM D 2583-06	50

## GENERAL INFORMATION

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.**

**For safe handling information on this product, consult the Safety Data Sheet (SDS).**

**Directions for use:****Surface Preparation:**

1. Store kits at 15 °C to 25 °C for at least 24 hours before beginning the chock pour
2. Bedplates and machinery should be at least @ 15 °C to ensure complete flow
3. Once the engine is in position, install sides and backs of dams for the chocks in a thickness of 12 to 70 mm. Check dams with a flashlight to assure tightness. When a thicker chock is required, use the multiple pour technique. Allow each pour to set and cool before proceeding. Subsequent pours should be made within 12 hours of previous pour
4. Apply general-purpose weather stripping to the front edge of bedplates that will be in direct contact with epoxy excess to eliminate cracking
5. Release agent or grease should be used in the prepared chock area and on exposed anchor bolts to facilitate chock removal for realignment
6. Position front dams using an angle iron large enough to permit a minimum of a 12.5 mm head above the bedplate surface. Position dams from 16 to 19 mm away from bedplate edges

**Mixing:**

Check Marine Chocking temperature and bedplate temperature. Add the required amount of hardener (per the reduction chart) to the contents of the resin can and mix with a heavy-duty drill for 1 to 5 minutes or until mixture is homogeneous. Mix at moderate speed, but do not allow a vortex to form. If the mixer vortexes, air will be drawn in which will cause bubbling of the chocking compound. Let the mixed product stand for 3 to 5 minutes to de-aerate

**Application Method:**

1. Pour chocks from one corner to maximize the escape of air and assure good surface contact. At 25 °C working time is approximately 10 to 15 minutes
2. Allow chocks to cure the following minimum times before torquing bolts and checking alignment:
  - 35 hours at 15 °C
  - 24 hours at 21 °C
  - 16 hours at 26 °C
  - 11 hours at 32 °C

**Technical Tips for Working With Epoxies**

Working time and cure depends on temperature and mass:

- The higher the temperature, the faster the cure
- The larger the mass of material, the faster the cure

To speed the cure of epoxies at low temperatures:

- Store epoxy at room temperature
- Pre-heat repair surface until warm to the touch

To slow the cure of epoxies at high temperatures:

- Mix epoxy in small masses to prevent rapid curing
- Cool resin/hardener component(s)

**Not for product specifications**

The technical data contained herein are intended as reference only and are not considered specifications for the product.

Product specifications are located on the Certificate of Analysis or please contact Henkel representative.

**Storage**

Store product in the unopened container in a dry location. Material removed from containers may be contaminated during use. Do not return liquid to original container. Storage information may be indicated on the product container labeling.

**Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties**

Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those recommended. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Conversions**

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\mu\text{m} / 25.4 = \text{mil}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{N/mm}^2 \times 145 = \text{psi}$   
 $\text{MPa} \times 145 = \text{psi}$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$

**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind,**

**including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage:** [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

#### Reference 2.4